

# TRANSFER COATING



<b>ARTICLE</b>	Silver Spring 2	<b>CUSTOMER</b>	Shanghai fair 2018
<b>MATERIAL</b>	Grey microfiber	<b>DATE</b>	13/6/2018
<b>COLOUR</b>	Grey	<b>MACHINE</b>	Lab coater
<b>PATTERN</b>	MLB 1308 A	<b>SAMPLE #</b>	

Process	Product	1	2	3	Operation Metrics
<b>Pre-skin</b>	PeVit™ XCB 5423	800			Viscosity~2500 cps 1x 0.15 mm, Dry @ 90°C, 3 min
	PeVit™ XMF 5498	200			
	PeVit™ XCL 5482	10			
	PeVit™ XVS 5491	X			
<b>Skin</b>	PeVit™ XCB 5424		900		Viscosity~2500 cps 1x0.20 mm, dry @ 90°C, 3 min
	PeVit™ XPG white		100		
	PeVit™ XPG black		30		
	PeVit™ XCL 5482		10		
	PeVit™ XVS 5491		X		
<b>Adhesion</b>	PeVit™ XPU 5444			1000	Viscosity~8000 cps 1x0.30 mm, dry @ 90°C, 5 min
	PeVit™ XCL 5482			20	
	PeVit™ XVS 5491			X	

PeVit™ is a registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.