

Wet-End



ARTICLE	BINDI	CLIENT	IILF 2019
MATERIAL	COW DYED CRUST	RECIPE NO.	IILF 1956WE1
QUANTITY	10 pieces	DATE	07 January 2019
% based on weight:	shaved weight 13 kg	COLOUR	SICULO TPX 19-1448
	substance 0.9/1.0 mm	TECHNICIAN	S.PANDYARAJAN / KALAIMANI

Process	%	kg	Product	Time	Comments
WETBACK	400	52	water,35°C		
	2	0,26	SELLATAN® CF-I		
	1	0,13	BORRON® SAF	30'	
	2	0,26	SELLASOL® NG Liq	30'	Check Wetback
	1	0,13	SELLASOL® SF		
Drain					
	300	39	water,30°C	10'	
Drain					
	100	13	water,35°C		
	1	0,13	SELLASOL® NG Liq	20'	
RETANNING & DYEING	4	0,52	SELLATAN® HAT Liquid		
	3	0,39	Gambier Powder		
	3	0,39	SELLATAN® TMC		
	3	0,39	SELLATAN® 4002		
	1	0,13	INVADERM® LU		
	0,3	0,039	SELLA® Fast Orange A		
	0,1	0,013	SELLA® Fast Yellow GT	45'	
FATLIQUORING	200	26	water,50°C		
	2	0,26	CORIPOL® BZE-N		
	2	0,26	CORIPOL® DX-1202		
	2	0,26	CORIPOL® SFC	45'	
	0,5	0,065	BORRON® SAF		
FIXING	1,5	0,195	Formic acid	10'+20'	
Drain					
	300	39	water,40°C		
	2	0,26	CORIPOL® GMT	20'	
Drain					

Cool Horse Up/Next Day
Do Samm/Then hot tumble at 55°C/2 Hrs
Then dry mill to reqd.softness

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

Wet-End



RECIPE NO. **IILF 1956WE1** CONTINUED

Process	%	kg	Product	Time	Comments
---------	---	----	---------	------	----------

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.