



Wet-End

Shoe & Leather Goods

ARTICLE **Solar, Lady Enveloppe FOC Suede**
MATERIAL **Nigerian Goats FOC**
QUANTITY **15** skins
% based on sammed weight substance **0.9-1.0** mm
weight: kg

CLIENT **IILF 2019**
RECIPE NO. **IILF1927WE**
DATE **25 January 2018**
COLOUR **SCARLATTO TPX 14-1064**
TECHNICIAN **Emilio Lindoni**

Process	%	kg	Product	Time	Comments
	300		water, 40°C		no shaving!
	1		BORRON® SE		
	1		oxalic acid	40'	
Drain					
	300		water, 40°C	10'	
Drain					
	200		water, 40°C		
	4		TANNESCO® CPR Liq	30'	
	2		CORIPOL® TR	30'	
	6		TANNESCO® FC		
	2		sodium formate	90'	automatic overnight
Drain				next morning	pH 4.0
	300		water, 40°C	10'	
Drain					
	200		water, 40°C		
	2		sodium formate	30'	
	0,5		sodium bicarbonate	40'	pH 5.5
Drain					
	300		water, 45°C	10'	
Drain					

continue on next page

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

Wet-End

Shoe & Leather Goods



RECIPE NO.

IILF1927WE

CONTINUED

Process	%	kg	Product	Time	Comments
	100		water, 45°C		
	5		MAGNOPAL® IPF		
	5		MAGNOPAL® SFT-F		
	2		CORIPOL® DX-1202	40'	
	8		SELLATAN® MBS Gran		
	4		SELLASOL® BC/7	60'	
	6		CORIPOL® DX-1202		
	6		CORIPOL® ESU	60'	
	4		MAGNOPAL® FIS	40'	
	2		formic acid	40'	
Drain					

cooling horse up overnight
 setting out hang to dry
 toggling buffing

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.