



Wet-End

Shoe & Leather Goods

ARTICLE	Vernicetta, Lady Bag Patent FOC			CLIENT	IILF 2019
MATERIAL	Sides Wet White			RECIPE NO.	IILF1929WE
QUANTITY	5	sides		DATE	26 January 2018
% based on weight:	shaved weight	substance	1,5 mm	COLOUR	SCARLATTO TPX 14-1064
	kg			TECHNICIAN	Fabio Zampinetti

Process	%	kg	Product	Time	Comments
	300		water, 35°C		
	0,5		oxalic acid		
	0,5		BORRON® SE	30'	pH 3.8
Drain					
	150		water, 30°C		
	5		TANNESCO® FC	60'	
	1		sodium bicarbonate		
	2		SELLASOL® NG Gran		
	2		CORIPOL® AV	60'	pH 5.5
Drain					
	300		water, 20°C	10'	
Drain					
	100		water, 30°C		
	6		MAGNOPAL® PGN		
	1,5		MAGNOPAL® TGR		
	2		MAGNOPAL® DP	30'	
	15		SELLATAN® HO Liq	30'	
	2,5		SELLA® Fast Yellow R		
	0,1		SELLA® Fast Orange A		
	15		SELLATAN® RP	120'	
	6		MAGNOPAL® PGN		
	1,5		MAGNOPAL® TGR		
	2		MAGNOPAL® DP	60'	dye through
	100		water, 50°C		
	4		CORIPOL® SB		
	3		CORIPOL® SV		
	3		CORIPOL® BZE-N		
	1		CORIPOL® ICL	30'	
	2		formic acid	20'	
	2		formic acid	20'	
	1		formic acid	20'	
Drain					

continue on next page

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

Wet-End

Shoe & Leather Goods



RECIPE NO. IILF1929WE CONTINUED

Process	%	kg	Product	Time	Comments
	300		water, 20°C		
	0,15		BORRON® SE	20'	
Drain					horse up overnight setting out vacuum 40°C 40" hang to dry staking

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.