



Wet-End

Shoe & Leather Goods

ARTICLE	DIOMEDE	CLIENT	TFL
MATERIAL	crust wb	RECIPE NO.	30
QUANTITY	sides	DATE	18 July 2022
% based on	dry weight	COLOUR	TPX 13-5304
weight:	kg	substance	1,6 mm
		TECHNICIAN	Simone Tempesti

Process	%	kg	Product	Time	Comments
	500		water, 40°C		
	1		CORIPOL GLH		
	0,3		BORRON® SAF	40'	
Drain					
	200		water, 35°C		
	4		TANIGAN PAK		
	2		sodium formate	20'	
	10		LEVOTAN RP		
	10		RETINGAN RLF		
	10		TANIGAN HO		
	10		TANIGAN LF-O liq. (3250)	20'	
	x		dyestuffs	90'	
	200		water, 50°C		
	10		LUBRITAN SPE		
	12		CORIPOL® EFN		
	8		CORIPOL® WKN	60'	
	2		formic acid	30'	
Drain					

Comments:

set out flesh side

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.