

# Wet-End



ARTICLE	VOLT	CLIENT	TFL ITALY
MATERIAL	NBT OX-HEIFER	RECIPE NO.	Article 7
QUANTITY	3 hides	DATE	31 August 2022
% based on	shaved weight	substance	1,3-1,4 mm
weight:	kg	COLOUR	TPX 13-4304
		TECHNICIAN	Fabio Zampinetti

Process	%	kg	Product	Time	Comments
Drain Wash	200		Water 45°C		
	0,3		BORRON® SAF		
	0,5		BLANCOROL® CGA		
	0,7		Acido Ossalico	10'	Ph= 3,00
Drain	100		Water 35°C		
	2		SELLATAN® CF New		
	1		CORIPOL® AT	30'	
	2		BLANCOROL® RC		
	5		Chrome		
	2		SELLASOL® FTF	90'	
	2		Sodium Formate	30'	
Drain	100		Water 35°C		AUT.O/N 5'X25'
			IN THE MORNING	5'	
Drain-Wash	120		Water 35°C		
	2		TANIGAN®PAK		
	2		Sodium Formate	45'	
	3		LEVOTAN AM	40	
Drain	50		Water 35°C		
	2		LEVOTAN® C01		
	1		CORIPOL® AT	10'	
	4		MAGNOPAL® RHN		
	2		LEUKOTAN® 1084	40'	
	7		TANIGAN®OS-N		

## Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.