

TRANSFER COATING



ARTICLE	14-0955	CUSTOMER	
MATERIAL	Base	DATE	10/05/2019
COLOUR	Yellow	MACHINE	Lab coater
PATTERN	Plastic paper	LOCATION	ATC

Process	Product	1	2	3	Operation Metrics
Pre-skin	PeVit XPU 5439	1000			Viscosity~3000 cps 1 x 0.15mm Dry @ 100°C, 3 min
	Roda policolor kiwi new	100			
	PeVit XCL 7190	20			
	PeVit XVS 5491	X			
	PeVit XMF 5495	5			
	PeVit XMF 5494	10			
Skin	PeVit XPU 7473	1000			Viscosity~5000 cps 1x0.20mm Dry @ 100°C, 5 min
	Pigment	100			
	PeVit XCL 7190	20			
	PeVit XVS 5491	X			
Adhesion	PeVit XPU 7501	1000			1x0.30mm
Pigment	PeVit XPG white	80			
	PeVit XPG yellow	20			

TRADEMARK® and TRADEMARK® are in registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.