

# Product Information

## Finishing



Edition 2019

RODA<sup>®</sup> Car P range – High performance, casein-free anionic pigment dispersions, in an aqueous phase

RODA <sup>®</sup> Car P	Pigment Type	Dry Content	3 Cycles Light Fastness (ISO 105-B06)		PVC Migration (ISO 15701)	30' Heat Resistance
			Full Shade	Pastel 10/90		
RODA <sup>®</sup> White P	Inorganic	69%	5	n.a.	5	> 300°C
RODA <sup>®</sup> Off White P	Inorganic	57%	5	n.a.	5	> 300°C
RODA <sup>®</sup> Lemon P	Organic	22%	5	4-5	5	250°C
RODA <sup>®</sup> Yellow P	Organic	20%	5	4	4-5	200°C
RODA <sup>®</sup> Green P	Organic	23%	4-5	5	4-5	200°C
RODA <sup>®</sup> Ochre P	Inorganic	50%	5	5	5	200°C
RODA <sup>®</sup> Orange P/N	Organic	20%	4-5	4-5	4-5	180°C
RODA <sup>®</sup> Red P	Organic	24%	5	4-5	4-5	200°C
RODA <sup>®</sup> Fuchsia P	Organic	21%	4-5	4-5	4-5	200°C
RODA <sup>®</sup> Red Violet P	Organic	21%	4	3	5	200°C
RODA <sup>®</sup> Brown P	Organic	19%	5	5	4-5	200°C
RODA <sup>®</sup> Orange Brown P	Inorganic	50%	5	5	5	> 180°C
RODA <sup>®</sup> Red Brown P	Inorganic	54%	5	5	5	> 300°C
RODA <sup>®</sup> Violet Brown P	Inorganic	60%	5	5	5	180°C
RODA <sup>®</sup> Violet P	Organic	20%	4-5	4-5	5	> 180°C
RODA <sup>®</sup> Blue P/N	Organic	29%	4	4-5	5	200°C
RODA <sup>®</sup> Blue SP/N P	Organic	20%	5	4-5	4	200°C
RODA <sup>®</sup> Black P	Inorganic	16%	5	5	5	> 300°C
RODA <sup>®</sup> Jet Black P	Inorganic	19%	5	5	5	> 300°C
RODA <sup>®</sup> Black SH P	Inorganic	21%	5	5	5	> 300°C

The light fastness evaluation is based on 5 degrees of grey-scale.

Data shown are typical values of our standard production; they must not be taken as commercial specifications. Quality specifications are available on request.

**Safety:** Please refer to our safety data sheets.

RODA<sup>®</sup> is a registered or filed trademark owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.