

Finishing

Sport Shoe Upper



CLIENT Fashion Colours Autumn Winter 20/21
 ARTICLE 9 - PLATA
 MATERIAL COW SIDE - ARGENTINA f.g.
 COLOUR TPX 19-4234 BLUE

RECIPE NO.
 BASED ON WE RECIPE NO.
 DATE
 TECHNICIAN

BU 4817
 FB18186
 MAR. 2019
 BORGIA ROBERTO

Product	1	2	3	4	5	6	Procedure
RODA® Lite 07 pigment mix	25						
water	100	400					
RODA® Penetrator IE 880	25						1) 2X SPRAY 5 gr sqf
RODA® Micro Bond A	100						APPLY RODA® Micro Lucent
RODA® Feel KTA 950		20					110°C - 100Kg by rotopress
RODA® Wax KCF 699		20					EMBOSS HAIRCELL 100°C - 100Kg
							2) 1X SPRAY 2 gr sqf
							IRON 100°C - 50Kg
Total	250	440	0	0	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.
 Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.
 We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.