Finishing

Shoe Lining

CLIENT	**TFL ITALIA**	RECIPE NO.	**BU 4889**
ARTICLE	**N°1 ZAMBESI**	BASED ON WE RECIPE NO.	
MATERIAL	**GOAT SKIN**	DATE	**JULY 2019**
COLOUR	**GREY SILVER - TPX 16-1305**	TECHNICIAN	**BORGIA ROBERTO**

Product	1	2	3	4	5	6	Procedure
RODA® Silver Top 578 SF	20						
RODA® Micro Bond A	100						1) 2X SPRAY on grain side
WATER	100	800					APPLY RODA® Micro Lucent
RODA® Penetrator IE 880	20						@ 100°c - 50Kg
SELLA® Derm M2 MIX	2						REST OVER NIGHT - STAKING
RODA® Feel N4		80					EMBOSS "CARTIER"
							DRY MILL OVER NIGHT
							conditioning in milling drum @ 40°C
							2) APPLY IN BY MILLING DRUM IN 1 HOUR
							THEN ONE HOUR NORMAL MILLING
Total	**242**	**880**	**0**	**0**	**0**	**0**	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.
We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.