Finishing

CLIENT

Automotive

RECIPE NO. Nr. 6

ARTICLE MUSTANG ORIENTED - NAPPA

BASED ON WE RECIPE NO.

MATERIAL Wet White - FG Grain

DATE

TECHNICIAN

COLOUR **DESIGN COLLECTION - MORGANITE**

Automotive Competence Team

Product	1	2	3	4	5	6	Procedure
Water	55	135					Stake
BAYDERM® Compact MLA	730						
RODA® Line AS	40						Basecoat:
RODA® Car Pigment Mix	160						1) 2 x Mega Star 25G: 9 g/sqft + 5 g/sqft
RODA® LINK 5777	15						
AQUADERM® Finish Matt A		600					
AQUADERM® Finish Gloss A		70					Stake
BAYDERM® Bottom DLV-N		30					
AQUADERM® Fluid E		15					Topcoat:
AQUADERM® Additive DF		70					2) 2 x Mega Star 25G: 3,0 g/sqft each
ACRYSOL™ RM 819-W Rheol.Mod.		х					
AQUADERM® XL DI 2		80					
							+
VISC: DIN Cup 4mm	50-55"	24-26"					
							_
							-
							-
							-
							<u> </u>
Total	1000	1000	0	0	0	0	<u>-</u>

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.