

Finishing Leather Goods



CLIENT **TFL**
 ARTICLE **N°14 CANDIED**
 MATERIAL **COW SIDE F.G.**
 COLOUR **TPX 17-1452**

RECIPE NO. **BU 5969**
 BASED ON WE RECIPE NO.
 DATE **FEB. 2023**
 TECHNICIAN **Borgia Roberto**

Product	1	2	3	4	5	6	Procedure
RODA®Lite 07 MIX	100		30				1) 2X-3X SPRAY
RODA®Pur 5101/N	600						
RODA®Pure Oil AA 4040	100						2) 1X SPRAY
WATER	200	300	500	200			
RODA®Pur ADX		100	250				3) 3X SPRAY
I.P.A.		100	70				IRON 90°C - 50 atm
RODA®Base AF-B/N			250				+ 2X SPRAY
RODA®Bind TLC 385			70				
EUDERM®Diepersion MA			100				4) 2X SPRAY
Aquaderm®X Biomer XL 7010			8	5			IRON 110°C - 50 atm
RODA®Wax KCF 699			50	50			DRY MILL TO EFFECT
RODA®Polipearl Copper			4				
RODA®Fix 5090				100			
RODA®Fix 5188/N Gloss				100			
RODA®Link 4009				20			
RODA®Pur 5008				20			
Total	1000	500	1332	495	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.