

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		200	0,000	Water水	40°C			
WETBACK回水		0,5	0,000	BORRON® SAF-A				
		0,5	0,000	BORRON® SE			45'	Check for proper wetback and then 查看回水状态
		0,2	0,000	PELTEC® AP			60'	
Drain控水								
		200	0,000	Water水	30°C		10'	
Drain控水								
		100	0,000	Water水	30°C			
		0,5	0,000	Formic acid甲酸			10'+15'	Check pH 3.2/3.3 BCG to Yellow
		2	0,000	SELLATAN® CF-A LIQ			20'	automatic overnight自动过夜
		4	0,000	chromosal B				morning pH=3.8 drain次日控水
RECHROMING		3		TANNESCO® HN Powder				
铬复鞣		1	0,000	CORIPOL® SG				
		3	0,000	SELLATAN® RL LIQ			75'	
BASIFICATION		1	0,000	sodium formate甲酸钠			30'	
提碱		1	0,000	sodium bicarbonate小苏打			2X15'+45'	Check pH 3.8/4.0 BCG To Green
Drain控水			0,000					
		100	0,000	Water水	30°C		10'	
Drain控水								
NEUTRALISATION		100	0,000	Water水	30°C			
中和		2	0,000	SELLASOL® NG LIQ				
		2	0,000	sodium formate甲酸钠			60'	
		1,5	0,000	sodium bicarbonate小苏打			2X10'+30'	Check pH 5.6/5.8 BCG to Deep Blue
		2	0,000	OROPON® DVP				
		1	0,000	CORIPOL® SG			60'	30'
		50	0,000	Water水	30°C			
RETANNING复鞣		3	0,000	LEUKOTAN™ 1084				
		2	0,000	LEVOTAN® L			30'	
		3	0,000	SELLASOL® PURE H			30'	
		3	0,000	SELLASOL® BC-N				
		5	0,000	SELLATAN® RL LIQ				
		3	0,000	TANIGAN® PURE T-A				
		3	0,000	GS Powder			60'	
		3	0,000	TANIGAN® OSO Liq			30'	
		2	0,000	BAYKANOL® SL			30'	Drain控水
DYEING染色		4		SELLA® STAR COPPER				Check proper dye penetration 检查染料渗透
FATLIQUORING 加脂		150		water水	50°C			
		4		LEVOTAN® L				
		4		CORIPOL® SLG-A				
		3		CORIPOL® MK-A				
		1		CORIPOL® PURE N				
		2		CORIPOL® BZE/N				
		3		CORIPOL® LC-A				
		0,5		BORRON® SAF-A				
		0,1		Preservative防腐剂			20'+40'	
		2		LEVOTAN® RP			20'	
		2		GS Powder			20'	
		100		water水	50°C			
		2		Formic acid甲酸			10'+20'	
FIXING固定		2		Formic acid甲酸			20'+30'	Check bath exhaustion and then 检查浴液耗尽然后
Drain控水								
		200		Water水	30°C		10'	
Drain控水								
		200		Water水	30°C		30'	
TOP FATLIQUORING加脂		1		CORIPOL® BZN				
		0,5		CORIPOL® PURE N				
		1		LEVOTAN® L				
		0,2		BORRON® SAF-A			30'	
FIXING固定		0,5		Formic acid甲酸			30'	
Drain控水								
		200		Water水	30°C		10'	
Drain控水								

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application..