

BU 6634

22 January 2026

GIRAUDO

Product	1	2	3	4	5	6	Procedure
WATER	50	500	300	800			1) 1 reverse coat(approx 8gr sq/ft) dry
RODA® Lite 07 mix	100		100				
RODA® Car B 34 /N	470		470				
EUDERM® X Grade MS/N	300		300				2) 1 spray coat, dry
RODA®Pur 64/N	100		100				
RODA® Feel S 5796	30		30				embossed 100°C at 250 bar 2 sec
RODA® Lac WG4		500					
RODA® Feel N4				200			3 1-2 spray coats, dry ,ironing on the top 125°C dry drum 3 hrs with RODA Feel N4
Total	1050	1000	1300	1000	0	0	

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.