

Wet End - Process Formulation (RETAN)



N°10 NINBO we.xlsx			Date:	7-Nov-2026
			Technician:	Gianni
Company:	TFL FW 27-28			
Type of Leather:	Shoe Upper & Leather Goods			Trial - N°:
Aim of Trial:	N°10 NIMBO			Color: 18-2920
			Piece count:	
Project - N°:				Substance: 1,1-1,2 mm
Material:	calf wb 小牛蓝皮			Weight:
% refer to:	shaved weight削匀重			Drum - N°:

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		300,00		Water水	40°C			
		1,00		Formic acid甲酸				
		0,30		BORRON® ADN			40	Drain控水
		100,00		Water水	40°C			
		3,00		TANNESCO® FC			30	
		1,00		CORIPOL® DX-1202			10	
		6,00		RETINGAN® LFC			30	
		5,00		chromosal B				
		5,00		BLANCOROL® RC			120	automatic overnight自动过夜
								次日morning pH=3,8 Drain控水
		150,00		Water水	35°C			
		3,00		SELLASOL® NG-A LIQ				
		1,00		sodium formate甲酸钠			30	
		0,30		sodium bicarbonate小苏打				
		4,00		LEVOTAN® L			60	pH: 4,6-4,8 Drain wash控水水洗
		80,00		Water水	30°C			
		1,00		MAGNOPAL® DP			10	
		6,00		BAYTIGAN® AR			30	
		2,00		CORIPOL® DX-1202			20	
		9,00		TANIGAN® MBO-A LIQ				
		2,00		TANIGAN® SR				
		5,00		RETINGAN® R7			60	
		100,00		Water水	50°C			
		0,50		Formic acid甲酸			30	Drain wash控水水洗
		100,00		Water水	50°C			
		3,00		CORIPOL® LEO				
		3,00		CORIPOL® DX-1202				
		2,00		LEVOTAN® L				
		0,50		BORRON® SAF-A			60	
		6,00		LEVOTAN® RP			30	
		0,50		Formic acid甲酸			30	Drain控水

Mechanical Operation:	Process Information:
set out,vacuum 240" 40°C 伸展, 真空40度4分钟	
	Running Time: 9 hrs 50 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for