

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		100,00	25,000	water水	50			
		2,00	0,500	BORRON® SE				
		0,50	0,125	acetic acid草酸			60	D/W控水/水洗
			0,000					
		100,00	25,000	water水	38			
		4,00	1,000	RETINGAN® LFC			30	
		1,00	0,250	CORIPOL® UFB-A			30	
		0,40	0,100	Formic Acid85%甲酸			10	pH3.2
		4,00	1,000	TANNESCO® HN GRAN				
		4,00	1,000	BLANCOL® AC			90	
		4,00	1,000	TANNESCO® FC			120	AUTOMATIC NIGHT自动过
			0,000					MORNING WASH次日水
		100,00		water水	40			
		1,50	0,375	CROMENO® BF			20	
		0,30	0,075	sodium bicarbonate小苏打			20	pH 5.0
		3,00	0,750	RETINGAN® R7				
		4,00	1,000	TANIGAN® PURE T-A			45	D/W控水/水洗
			0,000					
		80,00	20,000	water水	50			
		3,00	0,750	LEVOTAN® L			30	
		4,00	1,000	SELLASOL® FSU				
		4,00	1,000	RETINGAN® ZF PLUS				
		4,00	1,000	BAYTIGAN® AR			45	
		6,00	1,500	LEVOTAN® HPP				
		3,00	0,750	CORIPOL® AT				
		3,00	0,750	MAGNOPAL® IPF			40	
		2,00	0,500	RODA® WAX 5044				
		1,00	0,250	CORIPOL® PURE N				
		1,00	0,250	BORRON® SAF-A			40	
		1,70	0,425	SELLASET® BULE HN				
		0,20	0,050	SELLA FAST® GREY RLN 02				
		0,25	0,063	SELLA FAST® RED F			30	
		10,00	2,500	VEGTAN® M			45	
		4,00	1,000	MAGNOPAL® PGN-A			30	
		100,00	25,000	water水	50			
		3,00	0,750	Formic Acid85%甲酸			3*10+45	D/W控水/水洗
			0,000					
			0,000					
			0,000					
Mechanical Operation:					Process Information:			
HORSE UP,SETTING OUT, VACUUM 43°C 100SEC,HAGER 搭马, 伸展, 真空43度100秒, 挂晾干燥								
					Running Time:			11 hrs 25 min

Our application recommendations are in line with our current state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Our products are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical purposes.