

Finishing Leather Goods



CLIENT TFL
 ARTICLE N°10 GRAY
 MATERIAL COW F.G
 COLOUR TPX 13 - 0403

DATE
 RECIPE NO.
 BASED ON WE RECIPE NO.
 TECHNICIAN

SEPT. 2023
 BU 6097
 Borgia Roberto

Product	1	2	3	4	5	6	Procedure
RODA® Lite 07 MIX	50		50				1) 3X SPRAY
Water	400	100	300	150			
EUDERM® Prebottom RPN-N-C	150						2) 1X SPRAY
RODA® Cryl NP 87	70						EMBOSS "VIRGINIA"
RODA® Base AF-B/N	150		300				STAKING
RODA® Feel KTA 950			25				DRY MILL 8 hrs
ISODERM LA 300		200					LIGHT TOGGLE
RODA® Wax 4039/N			50				
RODA® Link PAX			5	5			3) 3X/4X SPRAY
RODA® Fix 5188/N Gloss				100			
RODA® Wax 2014				30			4) 2X SPRAY
RODA® Fix 1051/N				100			IRON 110°C - 50Kg
RODA® Link 4009				20			LIGHT MILLING
RODA® Pur 5008				20			VACUUM 70°C - 10"
Total	820	300	730	425	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.
 Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.
 We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.