

Finishing Shoe Upper

CLIENT	TFL
ARTICLE	N°14 SUBACQUEO
MATERIAL	COW SIDE F.G.
COLOUR	TPX 19-4028

RECIPE NO.
BASED ON WE RECIPE NO.
DATE
TECHNICIAN

Product	1	2	3	4	5	6	Procedure
RODA® Base 5103-A	500	500					
Water	500	500	350	350			1) 2X S
RODA® Poliperl Iridescent Blue		15					SANDB
RODA® Poliperl Micro Gold			5				2) 2X S
RODA® Wax 4001			100				
RODA® Cryl 108/N2			200				3) 2X S
RODA® Feel KTA 950			25				DRY M
RODA® Pure Luster 232			25	20			IRONIM
RODA® Pure Luster 682				40			4) 2X S
RODA® Pure Luster 1505				40			IRONIM
RODA® Pur 5427/N				130			LIGHT
RODA® Link PAX				6			VACUL
RODA® Feel Microsil				5			
Total	1000	1015	705	591	0	0	

Comments:

* Mix well together

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from the proper use of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore we cannot accept any liability. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.



MEMA 24046

20 September 2024
Maurizio Menichetti

are

PRAY

BLAST 80°C 30 atm

PRAY

PRAY

ILL TO EFFECT 1hrs

VG ROTO 120°C 70 atm

PRAY

VG ROTO 100°C 30 atm

MILLING

JM 50°C

from performing his own tests to determine the suitability
re comes within the customer's sphere of responsibility.