

Wet End - Process Formulation (RETAN)



N14 SUBACQUEO wet end.xlsx

Date:

27-Jun-2024

Technician:

Company: FASHION S/S 2026

Type of Leather:

Trial - N°:

Aim of Trial: N14 SUBACQUEO

Color:

19 4028

Piece count:

Project - N°:

Substance:

1.0/1.1

Material:

Weight:

% refer to: shaved weight削匀重

Drum - N°:

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		250,00	0,000	Water水	35			
		1,00	0,000	CORIPOL® FCT				
		0,50	0,000	BORRON® SAF-A			40	pH 3.8 Drain控水
		300,00	0,000	Water水	25		10	Drain控水
		150,00	0,000	Water水	35			
		6,00	0,000	CHROME 26/33%				
		3,00	0,000	TANNESCO® HN gran				
		2,00	0,000	SELLASOL® Pure M				
		1,50	0,000	CORIPOL® Pure LW			60	
		1,50	0,000	sodium formate甲酸钠			90	O/N Drain控水 pH 3.7
		150,00	0,000	Water水	35			
		1,50	0,000	TANIGAN® PAK-S				
		1,50	0,000	sodium formate甲酸钠			30	
		0,80	0,000	sodium bicarbonate小苏打			40	pH 4.8
		4,00	0,000	MAGNOPAL® PGN-A			45	Drain控水
		300,00	0,000	Water水	25		10	Drain控水
		80,00	0,000	Water水	30			
		1,00	0,000	MAGNOPAL® DP			10	
		5,00	0,000	MAGNOPAL® RHN-A			30	
		3,00	0,000	RETINGAN® R7				
		2,00	0,000	SELLASOL® Pure M				
		2,00	0,000	RETINGAN® LFC				
		3,00	0,000	mimosa				
		2,00	0,000	BAYKANOL® PR-A				
		2,00	0,000	BAYKANOL® TF-2N-C 01				
		1,60	0,000	SELLASET® Black BR				
		0,80	0,000	SELLA® Fast Navy A				
		0,50	0,000	SELLASET® Blue HN				
		1,00	0,000	CORIPOL® SG			90	
		100,00	0,000	Water水	50			
		4,00	0,000	CORIPOL® Pure LW				
		3,50	0,000	DRYWALK® FAT New				
		4,00	0,000	CORIPOL® UFB-A			60	
		2,80	0,000	Formic acid甲酸		3*10+30		pH 3.5 Drain控水
		50,00	0,000	Water水	50			
		0,20	0,000	SELLASET® Blue HN			20	
		0,50	0,000	Formic acid甲酸			20	Drain控水
		300,00	0,000	Water水	25		10	Drain控水

Mechanical Operation:

vacuum 45°C 120sec

真空45度120秒

Process Information:

Running Time:

9 hrs 25 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application.