Wet End - Process Formulation (RETAN)



N30 HOKUSAI Pre Ta	n wet end.xlsx	Date:	
		Technician:	
Company:	FASHION S/S 2026		
Type of Leather:		Trial - N°:	
Aim of Trial:	N30 HOKUSAI PRE-CURTUME WW MBO LIQ	Color:	
		Piece count:	
Project - N°:		Substance:	
Material:	PIKLE酸皮	Weight:	
% refer to:		Drum - N°:	

Operation	Add	%	Weight	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		150,00	in kg 0,000	Water水	24	(1 : X)	in min	
	+++	7,00	0,000	SALT盐	24			
		1,00	0,000	CORIPOL® SLG-A			5	pH: 3 Be: 8
	+++	1,00	0,000	CORIPOL SLG-A			3	pri. 5 Bc. 6
			0,000	FOR FUR裘皮			30	
			0,000	FORFUN表反			30	
		3,00	0,000	BAYKANOL® RFS LIQ			20	
		20,00	0,000	TANIGAN® MBO-A LIQ			20	
		4,00	0,000	LEVOTAN® RP				
				BAYKANOL® RFS LIQ				
		3,00	0,000	BAYKANUL RFS LIQ			040	VER CORTE
		2,00	0,000	CORIPOL® DX-1202			240	AON
DDAIN		10,00	0,000	TANIGAN® BNO LIQ	-		60	AUN
DRAIN		450.00	0,000	W I.	0.5			
		150,00	0,000	Water水	35		30	
		0,20	0,000	PREVENTOL ICL防霉剂			30	
	+++				+			
	_							
	+							
	+++							
	+++							

Mechanical Operation:	Process Information:
set out, vacuum dry 250" at 40°C	
伸展,真空40℃ 250秒	

Running Time:

6 hrs 25 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application.