



Wet End - Process Formulation (RETAN)

Copy of N°16 KLOBERT we.xlsx

Date:

Technician:

Company: COLLECTION SS 2027

Type of Leather:

Trial - N°:

Aim of Trial: nappa x-tan

Color:

Piece count:

Project - N°: 16 KLOBERT

Substance:

0,9-1

Material: calfx-tan X-Tan 小牛

Weight:

% refer to: shaved weight削匀重

Drum - N°:

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		300,00		Water水	30°C			
		1,00		CORIPOL® DX-1202				
		0,30		BORRON® ADN			20	
								Drain控水
		80,00		Water水	30°C			
		2,00		SELLASOL® NG-A LIQ				
		1,00		sodium formate甲酸钠				
		1,00		CORIPOL® SLG-A			20	pH:
		7,00		mimosa GS				
		5,00		TANIGAN® PURE T-A				
		15,00		TANIGAN® RLO-A LIQ				
		3,00		RETINGAN® LFC			60	
		1,00		BORRON® SAF-A				
		3,00		CORIPOL PURE LW				
		3,00		CORIPOL® SLG-I				
		2,00		CORIPOL AT			20	
		7,00		mimosa GS				
		5,00		TANIGAN® PURE T-A				
		15,00		TANIGAN® RLO-A LIQ			30	
		1,00		BAYKANOL® RT CONC				
		3,00		RETINGAN® LFC				
		x		dyestuffs染料			240	aut. Night自动过夜
		100,00		Water水	50°C			
		1,00		Formic acid甲酸			10	
		1,50		Formic acid甲酸			30	
								Drain控水
		300,00		Water水	45°C		10	
								Drain控水
		70,00		Water水	45°C			
		0,50		sodium bicarbonate小苏打				
		1,00		MAGNOPAL® DP			10	
		4,00		CORIPOL® SLG-A				
		6,00		CORIPOL® Pure LW				
		6,00		CORIPOL® AT				
		1,00		BORRON® SAF-A			90	
		6,00		TANIGAN® RLO-A LIQ			30	
		1,00		Formic acid甲酸			20	
								Drain控水

Mechanical Operation:

set out, vacuum dry 90" at 40°C
伸展，真空40度90秒

Process Information:

Running Time:

9 hrs 50 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical