



Wet End - Process Formulation (RETAN)

Copy of N°28 NEWMAN we.xlsx

Date:

Technician:

Company: Collection SS2027

Type of Leather: Shoe Upper & Leather Goods

Trial - N°:

Aim of Trial:

Color:

Piece count:

Project - N°: 28 NEWMAN

Substance:

Material: lambs australian origin澳洲羔羊

Weight:

% refer to: pickle weight + 50%酸皮重+50%

Drum - N°:

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		80,00		Water水	30°C			
		2,00		SELLASOL® NG-A LIQ				
		1,00		sodium formate甲酸钠				
		0,50		CORIPOL® SG			30	
		8,00		mimosa GS (light)				
		6,00		LEVOTAN® RP				
		5,00		TANIGAN® PURE T-A				
		9,00		TANIGAN® BNO LIQ				
		3,00		RETINGAN® LFC			60	
		1,00		BORRON® SAF-A				
		2,00		CORIPOL® AT				
		3,00		CORIPOL® MK-A				
		2,00		CORIPOL® LEO			20	
		1,00		BAYKANOL® RT CONC				
		3,00		RETINGAN® LFC				
		x		dyestuffs染料			180	automatic night自动过夜
		100,00		Water水	50°C			
		1,00		Formic acid甲酸			10	
		1,00		Formic acid甲酸			30	
								Drain控水
		300,00		Water水	45°C		10	
								Drain控水
		70,00		Water水	45°C			
		0,50		sodium bicarbonate小苏打				
		1,00		MAGNOPAL® DP			10	
		3,00		CORIPOL® MK-A				
		3,00		CORIPOL® LEO				
		3,00		CORIPOL® AT				
		1,00		BORRON® SAF-A			40	
		4,00		LEVOTAN® RP			40	
		1,00		Formic acid甲酸			20	
								Drain控水
		200,00		Water水	20°C			
		1,00		Formic acid甲酸			10	
								Drain控水

Mechanical Operation:

Process Information:

Running Time:

7 hrs 40 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical