

# Product Information

## Finishing



Edition 2016

### **RODA® Lite 07 – Pigment range (pigment dispersions)**

RODA® Lite	Pigment type	Dry content	1 Fakra Cycle Light Fastness (VDA 7502/2A)		PVC Migration (IUF 442)	30' Heat resistance
			Full shade	Pastell 10/90		
<b>Lemon 07</b>	Organic	18 %	8	8	4 – 5	> 150°C
<b>Yellow 07</b>	Organic	24%	7	8	5	180°C
<b>Ochre 07</b>	Inorganic	50%	8	8	5	> 180°C
<b>Orange 07</b>	Organic	24%	8	7	4 – 5	> 200°C
<b>Red 07</b>	Organic	24 %	7	8	5	> 180°C
<b>Orange Brown 07</b>	Inorganic	50%	8	8	5	> 180°C
<b>Red Brown 07</b>	Inorganic	62%	8	8	5	> 180°C
<b>Violet Brown 07</b>	Inorganic	60%	8	8	5	180°C
<b>Red Violet 07</b>	Organic	17%	7	7	5	180°C
<b>Blue 07</b>	Org./Inorg.	16%	8	8	5	> 150°C
<b>Black 07</b>	Inorganic	19%	8	8	5	> 300°C
<b>Black SH</b>	Inorganic	21%	8	8	5	> 300°C
<b>White 07</b>	Inorganic	57%	8	-	5	> 300°C
<b>White N</b>	Inorganic	69%	8	-	5	> 300°C

The light fastness evaluation follows VDA 75202/2A based on 8 degree of the blue scale.

Data shown are typical values of our standard production; they must not be taken as commercial specifications: Quality specifications are available on request.

**Safety** For safety information see the safety data sheet.

Regarding toxicological and ecological data see the safety data sheet of above product.

RODA® is a registered or filed trademark owned by or licensed to TFL in most countries.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application